# UL 746F

## STANDARD FOR SAFETY

Polymeric Materials – Flexible Dielectric Film Materials for Use in Printed Wiring Boards and Flexible Materials Interconnect Constructions

Documents
Document Sharing Hub

Full document details: UL 746F 2025

Documents
Document Sharing Hub

Full document details: UL 746F 2025

UL Standard for Safety for Polymeric Materials – Flexible Dielectric Film Materials for Use in Printed Wiring Boards and Flexible Materials Interconnect Constructions, UL 746F

Third Edition, Dated March 4, 2021

***Summary of Topics***

***This revision of ANSI/UL 746F dated June 27, 2025 includes the following changes in requirements:***

***– Clarification of the UL 94 VTM test method; Table 8.1 – Table 8.4, 8.1.4A – 8.1.4C, 8.1.13A, 8.3, 8.5.1.12, 8.6.12, 8.6.13, 8.7.17***

Text that has been changed in any manner or impacted by ULSE's electronic publishing system is marked with a vertical line in the margin.

The new and revised requirements are substantially in accordance with Proposal(s) on this subject dated April 18, 2025.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form by any means, electronic, mechanical photocopying, recording, or otherwise without prior permission of ULSE Inc. (ULSE).

ULSE provides this Standard "as is" without warranty of any kind, either expressed or implied, including but not limited to, the implied warranties of merchantability or fitness for any purpose.

In no event will ULSE be liable for any special, incidental, consequential, indirect or similar damages, including loss of profits, lost savings, loss of data, or any other damages arising out of the use of or the inability to use this Standard, even if ULSE or an authorized ULSE representative has been advised of the possibility of such damage. In no event shall ULSE's liability for any damage ever exceed the price paid for this Standard, regardless of the form of the claim.

Users of the electronic versions of UL's Standards for Safety agree to defend, indemnify, and hold ULSE harmless from and against any loss, expense, liability, damage, claim, or judgment (including reasonable attorney's fees) resulting from any error or deviation introduced while purchaser is storing an electronic Standard on the purchaser's computer system.

Documents
Document Sharing Hub

Full document details: UL 746F 2025

No Text on This Page

Documents
Document Sharing Hub

Full document details: UL 746F 2025

**MARCH 4, 2021**
(Title Page Reprinted: June 27, 2025)



# UL 746F

## Standard for Polymeric Materials – Flexible Dielectric Film Materials for Use in Printed Wiring Boards and Flexible Materials Interconnect Constructions

First Edition – May, 2006
Second Edition – January, 2012

**Third Edition**

**March 4, 2021**

This ANSI/UL Standard for Safety consists of the Third Edition including revisions through June 27, 2025.

The most recent designation of ANSI/UL 746F as an American National Standard (ANSI) occurred on June 27, 2025. ANSI approval for a standard does not include the Cover Page, Transmittal Pages, and Title Page.

Comments or proposals for revisions on any part of the Standard may be submitted to ULSE at any time. Proposals should be submitted via a Proposal Request in the Collaborative Standards Development System (CSDS) at https://csds.ul.com.

Our Standards for Safety are copyrighted by ULSE Inc. Neither a printed nor electronic copy of a Standard should be altered in any way. All of our Standards and all copyrights, ownerships, and rights regarding those Standards shall remain the sole and exclusive property of ULSE Inc.

**© 2025 ULSE Inc. All rights reserved.**

Documents
Document Sharing Hub

Full document details: UL 746F 2025

No Text on This Page

Documents
Document Sharing Hub

Full document details: UL 746F 2025

## CONTENTS

### INTRODUCTION

1 Scope ....5
2 Abbreviations ....5
3 Units of Measurement ....5
4 Measurement Accuracy and Testing Conditions ....5
5 References ....6
6 Supplementary Test Procedures ....6
7 Glossary ....7

### CONSTRUCTION

8 Flexible Dielectric Material Test Programs and Sample Requirements ....13
8.1 General ....13
8.2 Direct support requirements (DSR) ....23
8.3 Polyimide ANSI-like flammability program ....24
8.4 Base materials (Dielectric film material) ....24
8.5 Conductor adhesives and conductors ....27
8.6 Bonding film (supported and unsupported) and internal bonding materials ....29
8.7 Cover material (coverlay, coverfilm and covercoat) ....31
8.8 Flexible material combinations and flexible mass laminate ....33

### PERFORMANCE

9 Short Term Performance Profile Tests ....36
10 Long Term Thermal Aging Tests ....36
11 Flammability Tests ....36
12 Microsection Analysis ....36
12.1 General ....36
12.2 Test samples ....37
12.3 Micro-etching the sample surface ....38
12.4 Material and test pattern parameter examination ....38
13 Thermal Stress Test ....38
13.1 Purpose ....38
13.2 Compliance criteria ....38
13.3 Test samples ....38
13.4 Test apparatus and material ....39
13.5 Procedure ....39
13.6 Data collection ....40
14 Delamination Test ....41
14.1 Purpose ....41
14.2 Compliance criteria ....41
14.3 Test samples ....41
14.4 Apparatus or material ....42
14.5 Procedure ....42
14.6 Data collection ....43
15 Bond Strength Test ....44
15.1 Purpose ....44
15.2 Compliance criteria ....44
15.3 Test samples ....44
15.4 Apparatus or material ....44
15.5 Procedure ....45
15.6 Data collection ....47

AVA Documents
Document Sharing Hub
Full document details: UL 746F 2025

16 Dissimilar Dielectric Materials Thermal Cycling Test ..... 48
16.1 Purpose ..... 48
16.2 Compliance criteria ..... 48
16.3 Test samples ..... 48
16.4 Apparatus ..... 49
16.5 Procedure ..... 49
17 Ambient-bend Test ..... 49
17.1 Purpose ..... 49
17.2 Compliance criteria ..... 49
17.3 Test samples ..... 50
17.4 Apparatus or material ..... 51
17.5 Procedure ..... 51
17.6 Data collection ..... 52
18 Cold-Bend Test ..... 53
18.1 Purpose ..... 53
18.2 Compliance criteria ..... 53
18.3 Test samples ..... 53
18.4 Apparatus or material ..... 53
18.5 Procedure ..... 54
18.6 Data collection ..... 55
19 Repeated Flexing Test ..... 55
19.1 Purpose ..... 55
19.2 Compliance criteria ..... 55
19.3 Test samples ..... 55
19.4 Apparatus or material ..... 56
19.5 Procedure ..... 57
19.6 Data collection ..... 58
20 Cover Material Lamination Test ..... 58
20.1 Purpose ..... 58
20.2 Compliance criteria ..... 58
20.3 Test samples ..... 58
20.4 Apparatus or material ..... 59
20.5 Procedure ..... 59
20.6 Data collection ..... 60

**MARKINGS**

21 Details ..... 60

**SUPPLEMENT SA – FOLLOW-UP INSPECTION**

SA1 Scope ..... 63
SA2 Glossary ..... 63
SA3 Responsibility of the Manufacturer ..... 64
SA4 Responsibility of the Field Representative ..... 64
SA5 Selection of Samples for Follow-Up Testing ..... 65
SA6 Follow-Up Test Program ..... 65

Documents
Document Sharing Hub
Full document details: UL 746F 2025

## INTRODUCTION

### 1 Scope

1.1 Flexible materials shall be defined as films or materials exhibiting flexible properties.

1.2 These requirements cover short term and long term test procedures to be used for the evaluation of flexible material, film, base material, conductor adhesive material, bonding film, cover lay, and other thin film materials used for parts intended for specific applications in end products.

1.3 Together with the Standards mentioned in the Supplementary Test Procedures, Section 6, these requirements provide data with respect to the physical, electrical, flammability, thermal, and other properties of the materials under consideration and are intended to provide guidance to the material manufacturer, the fabricator, the end product manufacturer, safety engineers and other interested parties.

1.4 Compliance with these requirements does not indicate the product is acceptable for use as a component of an end product without further evaluation.

1.5 These requirements do not apply to the evaluation of rigid industrial laminates having a thickness greater than 0.25 mm (0.010 inch). For materials with thicknesses greater than 0.25 mm refer to the Standard for Polymeric Materials – Industrial Laminates, Filament Wound Tubing, Vulcanized Fibre, and Materials Used in Printed Wiring Boards, UL 746E.

1.6 For constructions and materials not specifically addressed in this Standard:

- The printed wiring board should provide safeguards not less than that generally afforded by this document and the principles of safety contained herein. This includes printed wiring boards with technologies, materials, or methods of construction, including the manufacturing process, not specifically addressed in this document.

- Propose for discussion with the Technical Committee the need for additional detailed requirements to address a new situation in a timely manner.

### 2 Abbreviations

2.1 The acronym "FMIC" appears throughout this Standard, and stands for "Flexible Materials Interconnect Construction." See 7.57 for the definition of FMIC.

2.2 The acronym "MOT" appears throughout this Standard, and stands for "Maximum Operating Temperature." See 7.70 for the definition of MOT.

2.3 The acronym "RTI" appears throughout this Standard, and stands for "Relative Thermal Index." See 7.81 for the definition of RTI.

### 3 Units of Measurement

3.1 Values stated without parentheses are the requirement. Values in parentheses are explanatory or approximate information.

### 4 Measurement Accuracy and Testing Conditions

4.1 A measuring device used to perform the tests required by this Standard shall be capable of measuring the specified parameter with an accuracy within 10 percent of the measured parameter.

AVA Documents
Document Sharing Hub
Full document details: UL 746F 2025

4.2 Prior to all tests, subject all samples to a stabilization period in accordance with the Standard Practice for Conditioning Plastics for Testing, ASTM D618, and the Standard for Plastics – Standard Atmospheres for Conditioning and Testing, ISO 291, for a minimum of 40 hours at 23 ±2 °C (73.4 ±3.6 °F) and 50 ±10 percent relative humidity, unless specified otherwise in the individual test method.

4.3 During the test, the standard atmospheric conditions surrounding the samples shall be 25 °C ±10 °C (77 °F ±18 °F) and 50 ±10 percent relative humidity, unless specified otherwise in the individual test method.

4.4 Once samples are removed from the thermal or humidity pre-conditioning environment, samples shall be cooled in the desiccator for at least 4 hours at room temperature and tested within 30 minutes after removal from the desiccator.

## 5 References

5.1 Any undated reference to a code or standard appearing in the requirements of this standard shall be interpreted as referring to the latest edition of that code or standard.

5.2 The following publications are referenced in this Standard:

ASTM D 374 – Standard Test Methods for Thickness of Solid Electrical Insulation

ASTM D 618 – Standard Practice for Conditioning Plastics for Testing

ASTM D 5423 – Standard Specification for Forced-Convection Laboratory Ovens for Evaluation of Electrical Insulation

ASTM D 5374 – Standard Test Method for Forced-Convection Laboratory Ovens for Evaluation of Electrical Insulation

ASTM E 3 – Standard Guide for Preparation of Metallographic Specimens

IPC TM-650 2.1.1 – Microsectioning Manual and Semi or Automatic Method

ISO 291 – Standard for Plastics – Standard Atmospheres for Conditioning and Testing

## 6 Supplementary Test Procedures

6.1 These requirements are intended to be used in conjunction with the following requirements or standards:

a) The Standard for Tests for Flammability of Plastic Materials for Parts in Devices and Appliances, UL 94, contains methods for evaluating the flammability of polymeric materials used for parts in electrical equipment.

b) The Standard for Polymeric Materials – Short Term Property Evaluations, UL 746A, contains short term test procedures to be used for the evaluation of materials used for parts intended for specific applications in electrical end products.

c) The Standard for Polymeric Materials – Long Term Property Evaluations, UL 746B, contains long term test procedures to be used for the evaluation of materials used for parts intended for specific applications in end products.

d) The Standard for Polymeric Materials – Use in Electrical Equipment Evaluations, UL 746C, contain programs for evaluating polymeric materials. UL 746C is intended for the evaluations of polymeric materials in specific applications in end products.

Documents
Document Sharing Hub
Full document details: UL 746F 2025

e) The Standard for Polymeric Materials – Industrial Laminates, Filament Wound Tubing, Vulcanized Fibre, and Materials Used in Printed Wiring Boards, UL 746E, contain programs for evaluating polymeric materials. UL 746E is intended for the evaluation of polymeric materials in specific applications in printed wiring boards.

f) The Standard for Printed Wiring Boards, UL 796, contains the minimum performance requirements for printed wiring boards.

g) The Standard for Flexible Materials Interconnect Constructions, UL 796F, contains the minimum performance requirements for flexible printed wiring boards and interconnect constructions.

## 7 Glossary

7.1 For the purposes of this Standard, the following definitions apply.

7.2 ADHESIVE – A substance such as glue or cement used to join, bond, or fasten materials or objects together.

7.3 ADHESIVELESS – Sputtered on or Cast on film. Adhesiveless does not include Laminated materials.

7.4 AS-RECEIVED – Samples in an unconditioned state, prior to being subject to conditioning, or without a history of conditioning.

7.5 ASSEMBLY SOLDERING PROCESS – The process used for soldering components to a printed wiring board during the assembly process. The soldering process may include but is not limited to reflow, wave, selective soldering or other equivalent soldering techniques.

7.6 BASE DIELECTRIC MATERIAL – An organic or inorganic dielectric barrier material, used to support conductor material.

7.7 BASE MATERIAL – An organic or inorganic insulating material used to support a pattern of conductor material, with or without integral adhesive material, with or without integral conductor material.

7.8 BASE MATERIAL THICKNESS – The thickness of the base dielectric material excluding conductive foil or material deposited on the surfaces. If an adhesive is used for the base material, the adhesive thickness and number of sides is indicated separately.

7.9 BONDING FILM – The layer of insulation used to bond discrete layers during lamination of multilayer flexible printed wiring board constructions. A general term used to describe bondply and freefilm. See also Bondply and Freefilm.

7.10 BONDING LAYER – An adhesive layer used to bond discrete layers during lamination.

7.11 BONDPLY – See Bonding Film.

7.12 BUILD-UP THICKNESS – Overall thickness of a combination of materials. Unless otherwise indicated, the build-up thickness will refer to the overall thickness in the area of a flexible material where no internal or external conductor material resides.

7.13 CALCULATED THICKNESS – A thickness value determined by adding suggested material component thicknesses, or a thickness value determined by adding or subtracting one measured value to or from another measured value.

AVA Documents
Document Sharing Hub

Full document details: UL 746F 2025

7.14 CAST ON COPPER – Resin is cast onto copper and then polymerized (cured). The process may require a “multilayer” resin to manufacture a double sided clad material.

7.15 CIRCUIT – Electrical devices and elements interconnected to perform a desired electrical function.

7.16 CIRCUITRY LAYER – Conductor layer or plane in or on an interconnect construction or printed board.

7.17 CLAD MATERIAL – Base material or base dielectric material with conductor material attached.

7.18 CLADDING – A deposited or plated metallic layer or laminated foil used for its protective and/or electrical properties. See Conductive Foil, 7.22.

7.19 COATING – A non-metallic substance applied by some process, such as dipping, curtain coating, film laminating, screening, spraying, or melt-flow.

7.20 CONDITIONING – The time related exposure of a test samples to a specified environment prior to or after testing and before evaluation.

7.21 CONDUCTIVE (ELECTRICAL) – The ability of a substance or material to conduct electricity.

7.22 CONDUCTIVE FOIL – A thin metal sheet intended for forming a conductor pattern on a base material.

7.23 CONDUCTOR – A single conductive in a conductive pattern.

7.24 CONDUCTOR ADHESIVE – Adhesive material used to attach conductor material to a base material, or base dielectric material.

7.25 CONDUCTOR AVERAGE TRACE WIDTH – The average width of a length of conductor trace.

7.26 CONDUCTOR BASE WIDTH – The width of a conductor at the interface of the conductor material and base material. See also Conductor Width.

7.27 CONDUCTOR LAYER – The total conductive pattern formed on one side of a single layer of a base material. (This may include all or a portion of ground and voltage planes.)

7.28 CONDUCTOR MATERIAL – An organic or inorganic substance capable of transmitting electricity, used for circuit conductors, including but not limited to copper, tin, nickel, gold, copper paste, silver paste, carbon paste, ruthenium oxide paste, etc.

7.29 CONDUCTOR PATTERN – The path, design, or configuration of conductor material on the base material, including but not limited to conductor traces, lands, through-holes, and vias.

7.30 CONDUCTOR THICKNESS – The thickness of the conductor and additional metallic platings or coatings, excluding non-conductive coatings.

7.31 CONDUCTOR TRACE – A linear conductor path of a conductor circuit.

7.32 CONDUCTOR WIDTH – The width of the conductor as viewed from a top view or at the plane of the surface of a base material, whichever is less. See Conductor Base Width.

Documents
Document Sharing Hub
Full document details: UL 746F 2025

7.33 CONSTRUCTION – A variation in flexible materials build-up, including but not limited to film, adhesive, base material, bonding film, cover lay, dielectric material, laminate, prepreg, or other insulation materials. Variations include singlelayer, multilayer, flexible, flex-to-install, rigid, and multilayer flex/rigid composite constructions.

7.34 CONTINUITY – An uninterrupted path for the flow of electrical current in a circuit.

7.35 CONVERTOR – Manufacturer who prepares materials, such as lamination of copper, adhesive, and base dielectric material for use in the fabrication of flexible materials.

7.36 CORE MATERIAL – The innermost material, interconnect construction, or printed wiring board which may be used to support a subsequent layer or layers of dielectric material and conductor pattern. Core material may be an organic or inorganic material, with or without integral dielectric material. Core material may be referred to as substrate material.

7.37 COVERCOAT – A material deposited as a liquid onto the circuitry that subsequently becomes a permanent dielectric coating. See Cover Material, 7.41.

7.38 COVERFILM – A film made from:

a) A homogenous, single component chemistry;

b) Separate layers of generically similar chemistries; or

c) A composite blend of chemistries.

See Cover Material, 7.41.

7.39 COVERLAY – Film and adhesive made from separate layers of generically different chemistries. See Cover Material, 7.41.

7.40 COVERLAY ADHESIVE – Adhesive used with film to prepare coverlay.

7.41 COVER MATERIAL – A thin dielectric material used to encapsulate circuitry, most commonly for flexible circuit applications. See Covercoat, 7.37, Coverfilm, 7.38, and Coverlay, 7.39.

7.42 CURRENT – The flow or movement of electrons in a conductor as a result of voltage difference between the ends of the conductive path.

7.43 DECLAD – A dielectric material from which the foil or conductive material has been removed by etching or other means.

7.44 DELAMINATION – A planar separation of materials between layers (i.e., separation between conductor and base material, bonding film and base material, cover film and conductor, etc.).

7.45 DIELECTRIC – A material capable of high resistance to the flow of electrical current and capable of being polarized by electric field.

7.46 DOUBLE-SIDED – A flexible material with a conductive layer on the two external sides of the base dielectric material.

7.47 END-PRODUCT – An individual part or assembly in its final completed state. See End-Use Product.

7.48 END-USE PRODUCT – A device or appliance in which an FMIC is installed as a component.

AVA Documents
Document Sharing Hub
Full document details: UL 746F 2025

7.49 ETCHANT – A solution used to remove the unwanted portions of material from a base dielectric material or interconnect construction by a chemical reaction.

7.50 ETCHED – A laminate material in which the conductive layer has been removed by a chemical process.

7.51 ETCHING – The chemical, or chemical and electrolytic, removal of unwanted portions of conductive or resistive material.

7.52 EXTERNAL LAYER – The conductor pattern on the external surface of the interconnect construction.

7.53 FABRICATOR – A manufacturer, alternate manufacturer, subcontractor, or multi-site processor who may form the pattern of conductive material, laminate, coat, or process the materials for production of an interconnect construction or FMIC.

7.54 FILM – A sheet, thin coating, or membrane material having a thickness not greater than 0.25 mm (0.010 inch).

7.55 FLAMMABILITY RATED ONLY – A flexible material intended for use where the construction shall be evaluated for a flammability classification only, and the thermal, mechanical, and electrical capacity of the materials is not of concern and only the flammability classification of the resulting FMIC is of concern in the end-use product.

7.56 FLEXIBLE MATERIALS INTERCONNECT CONSTRUCTION – A sub-category interconnect construction intended for use where some portion of the interconnect construction shall be subject to flexing in the end-use product application. See the Standard for Flexible Materials Interconnect Construction, UL 796F.

7.57 FMIC – See Flexible Materials Interconnect Construction.

7.58 FOIL LAMINATION – A process for bonding a conductive foil to a dielectric base material or interconnect construction.

7.59 FREEFILM – An adhesive layer used to bond discrete layers during lamination of multilayer flexible printed wiring board constructions. See Bonding Film, Bondply, and Unsupported Bonding Film.

7.60 GRADE – A designation arbitrarily assigned to a material by the material manufacturer, converter, or vendor.

7.61 INCLUSIONS – Foreign particles, metallic or nonmetallic, entrapped (cannot be wiped off with a cloth) in the specified material and were not intended as part of the material formulation.

7.62 INFRARED REFLOW (IR) – Melting of platings such as tin/lead or remelting of solder using infrared heat as the primary source of energy.

7.63 INTERCONNECT CONSTRUCTION – An integral combination of film, adhesive, base material, conductor, bonding film, cover lay, dielectric material, and other insulation material, fabricated to form point-to-point connections in a predetermined arrangement. The interconnect construction does not include stiffener or adhesive (external bonding) materials.

7.64 INTERNAL LAYER – A conductor pattern contained entirely within a multilayer interconnect construction.

Documents
Document Sharing Hub
Full document details: UL 746F 2025

7.65 LAMINATE (n.) – A product made by bonding together two or more layers of material.

7.66 LAMINATE THICKNESS – The thickness of the base dielectric material (not including adhesive thickness) in a single-sided or double-sided singlelayer metal-clad base material.

7.67 LAMINATED – Typically a “Multilayer” resin build up and then laminated to copper. One option is to start with a prepolymerized film, the same as used for cast on type, and build up other types of resin, typically thermoplastic. The thermoplastic layer can be considered to be an adhesive, to hold the film to the copper.

7.68 LAMINATING ADHESIVE – A thin film, coating, or membrane material used to laminate multilayer FMIC’s and printed wiring boards.

7.69 LAYER-TO-LAYER SPACING – The thickness of dielectric material between adjacent conductor planes (i.e., the physical distance between adjacent conductor planes).

7.70 MAXIMUM OPERATING TEMPERATURE (MOT) – The maximum operating temperature is the maximum continuous use temperature that the FMIC may be exposed to under normal operating conditions.

7.71 METAL-CLAD BASE MATERIAL – Base material with integral metal conductor material on one or both sides with or without adhesive.

7.72 MULTILAYER – Interconnect construction category that consists of alternate layers of conductor and dielectric materials laminated or bonded together, including at least three conductor layers separated by two dielectric layers, with at least one internal conductor layer.

7.73 PATTERN – The configuration of conductive and nonconductive materials on a base dielectric material.

7.74 PERFORMANCE LEVEL CATEGORIES (PLC) – An integer defining a range of test values for a given electrical or mechanical property test.

7.75 PLATING (n.) – Chemical or electrochemical deposition of metal on an entire surface or on a conductive pattern.

7.76 PLATING-UP – The electrochemical deposition of a conductive material on a base dielectric material taking place after the base dielectric material has been made conductive.

7.77 PREPREG – A sheet of material impregnated with a resin cured to an intermediate stage (B-stage resin).

7.78 PRINTED (CIRCUIT) BOARD – A printed board produced from rigid industrial laminate material that provides point-to-point connections and printed components in a predetermined arrangement. See the Standard for Printed Wiring Boards, UL 796.

7.79 PRINTED WIRING BOARD – See Printed (Circuit) Board.

7.80 REINFORCEMENT MATERIAL – Any material (i.e. fibrous, continuous, sheet, etc.) capable of enhancing the base material mechanical or physical performance.

7.81 RELATIVE THERMAL INDEX (RTI) – Maximum service temperature for a material, where a class of critical property will not be unacceptably compromised through chemical thermal degradation over the

AVA Documents
Document Sharing Hub
Full document details: UL 746F 2025

reasonable life of an electrical product, relative to a reference material having a confirmed, acceptable corresponding performance defined RTI.

7.82 RIGID – A sub-category construction intended for use where no portion of the interconnect construction shall be subject to flexing, bending, or flex-to-install in the end-use product application.

7.83 RIGID INDUSTRIAL LAMINATE – Fibrous reinforcement material impregnated or coated with a thermosetting resin binder, and consolidated under high temperature and pressure into a dense solid product.

7.84 RIGID PRINTED WIRING BOARD – A printed wiring board produced using rigid base dielectric materials.

7.85 ROLL MATERIAL – Flexible materials supplied on a supporting core for the purposes of off-winding for further processing.

7.86 SHEET MATERIAL – Flexible materials supplied cut to processing dimensions for further processing. May have been prepunched.

7.87 SINGLELAYER – Singlelayer flexible constructions are double-sided constructions with one layer of dielectric materials(s) separating the conductor planes, and single-sided constructions with a single conductor plane on one side of a dielectric material(s).

7.88 SINGLE-SIDED – Flexible material with conductive layer on one side of the base dielectric material(s).

7.89 SPUTTERED ON – Metallized pre-polymerized (cured) film. Typically the resin is a thermoset, but may be a thermoplastic.

7.90 STIFFENER – An organic or inorganic material used to provide support or strength to interconnect constructions as part of an FMIC.

7.91 SUBSTRATE – See Base Material.

7.92 SUPPORTED BONDING FILM – A combination of film with integral adhesive on two sides, and a dielectric material used to bond discrete layers during lamination of multiplayer flexible constructions and printed wiring boards. See also Bondply, Bonding Film, and Unsupported Bonding Film.

7.93 TEMPERATURE PROFILE – The depiction of the temperatures a select point traverses as it passes through a process involving multiple temperatures and dwell times.

7.94 TEST PATTERN – The conductor pattern intended for test and inspection purposes.

7.95 TEST SAMPLE – A complete (or portion of a) production flexible material formed by the production process incorporating specific features.

7.96 UL/ANSI TYPE MATERIAL – A specific type designation for materials defined in this Standard as having certain base material, resin, thermal index and profiles of minimum performance.

7.97 UNCLAD – A dielectric material without foil or conductive material (never copper clad.)

Documents
Document Sharing Hub
Full document details: UL 746F 2025

7.98 UNSUPPORTED BONDING FILM – A coating or membrane adhesive material used to bond discrete layers during lamination of multilayer constructions, FMICs and printed wiring boards. See also Bonding Film, Bondply, Freefilm and Supported Bonding Film.

7.99 VOID – The absence of metallic or nonmetallic substance in a localized area, in or on an interconnect construction or FMIC.

7.100 X-AXIS – A reference axis, usually horizontal or left-to-right direction in a two dimension coordinate system. The x and y axes are usually perpendicular to one another in a two or three dimension coordinate system.

7.101 Y-AXIS – A reference axis, usually vertical or bottom-to-top direction in a two dimension coordinate system. The x and y axes are usually perpendicular to one another in a two or three dimension coordinate system.

7.102 Z-AXIS – The axis perpendicular to the plane created by the x and y reference axes. This axis usually refers to the thickness of a flexible material.

## CONSTRUCTION

## 8 Flexible Dielectric Material Test Programs and Sample Requirements

### 8.1 General

8.1.1 The test programs are divided into parts 1) Identification and Flammability, 2) Performance Profile and RTI, and 3) Metal Clad testing to evaluate the dielectric base film, bonding film, cover material, and other thin insulation materials.

a) Generic RTI values for dielectric materials based on field-test performance and chemical structure are listed in Section 7 of the Standard for Polymeric Materials – Long Term Property Evaluations, UL 746B.

b) Table 8.1 covers the evaluation to determine the material general composition and the flammability characteristics.

c) Table 8.2 covers the evaluation to determine the material RTI and profile of performance index.

d) Table 8.3 covers the evaluation to determine the acceptability of the metal clad film to be used in the construction of flexible printed wiring boards or flexible interconnect material constructions.

e) Table 8.4 covers the evaluation to determine the acceptability of flexible material combinations and flexible mass laminate test program and sample requirements

f) Table 8.5 covers the evaluation of direct support

g) Table 8.6 lists sample thickness tolerance.

Documents
Document Sharing Hub
Full document details: UL 746F 2025

**Table 8.1**
**Dielectric Film Material Identification and Flammability Test Program and Sample Requirements**

| Property | Sample dimensions length by width, mm (inch) | Film thickness | Adhesive thickness | Minimum number of samples | Applicable materials | For method refer to: |
|---|---|---|---|---|---|---|
| Identification and Flammability Tests | | | | | | |
| Infrared Analysis (IR) Film only | 125 x 13 (5 x 0.5) | Max | – | 5 | F, B, C, CF | UL 746F, 8.1.4, UL 746A |
| Infrared Analysis (IR) Adhesive only[a,b] | 125 x 13 (5 x 0.5) | – | Max | 5 (or 50 g) | FA, B, C, CF | UL 746F, 8.1.4, UL 746A |
| Infrared Analysis (IR) Film and Adhesive[a,b] | 125 x 13 (5 x 0.5) | Max | Max | 5 | FA, B, C, CF | UL 746F, 8.1.4, UL 746A |
| Thermogravimetric Analysis (TGA)[5] | 125 x 13 (5 x 0.5) | Max | – | 5 | F, B, C, CF | UL 746F, 8.1.4, UL 746A |
| Flammability Vertical[c] | 125 x 13 (5 x 0.5) | Min | – | 20 | F, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Vertical[c] | 125 x 13 (5 x 0.5) | Max | – | 20 | F, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Vertical[c] | 125 x 13 (5 x 0.5) | Min | Min | 20 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Vertical [c] | 125 x 13 (5 x 0.5) | Min | Max | 20 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Vertical[c] | 125 x 13 (5 x 0.5) | Max | Min | 20 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Vertical[c] | 125 x 13 (5 x 0.5) | Max | Max | 20 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability VTM[c] | 200 x 50 (8 x 2) | Min | – | 20 | F, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability VTM[c] | 200 x 50 (8 x 2) | Max | – | 20 | F, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability VTM[c] | 200 x 50 (8 x 2) | Min | Min | 20 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability VTM[c] | 200 x 50 (8 x 2) | Min | Max | 20 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability VTM[c] | 200 x 50 (8 x 2) | Max | Min | 20 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability VTM[c] | 200 x 50 (8 x 2) | Max | Max | 20 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Horizontal[c] | 125 x 13 (5 x 0.5) | Min | – | 6 | F, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Horizontal[c] | 125 x 13 (5 x 0.5) | Max | – | 6 | F, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Horizontal[c] | 125 x 13 (5 x 0.5) | Min | Min | 6 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Horizontal[c] | 125 x 13 (5 x 0.5) | Min | Max | 6 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |
| Flammability Horizontal[c] | 125 x 13 (5 x 0.5) | Max | Min | 6 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |

**Table 8.1 Continued on Next Page**

Documents
Document Sharing Hub
Full document details: UL 746F 2025

## Table 8.1 Continued

| Property | Sample dimensions length by width, mm (inch) | Film thickness | Adhesive thickness | Minimum number of samples | Applicable materials | For method refer to: |
|---|---|---|---|---|---|---|
| Flammability Horizontal[c] | 125 x 13 (5 x 0.5) | Max | Max | 6 | FA, B, C, CF | UL 746F, 8.1.4, UL 94 |

Material Types:

F – Base Dielectric Film (film only, no adhesive. Includes adhesiveless “sputtered” or “cast on” materials.)

FA – Adhesive Coated Base Dielectric Film (film and adhesive)

B – Bonding Film (film and adhesive or adhesive only)

C – Cover material (film and/or adhesive, not intended to be used as a dielectric barrier)

CF – Coverfilm (film only, no adhesive)

NOTES:

1. All the samples shall be in the machine (grain) longitudinal direction unless specified otherwise.
2. All the samples shall be double sided unless single sided material is intended for production.
3. All the samples are to be prepared declad by completely etching a metal clad sheet, where applicable.
4. Infrared Analysis may be performed using Attenuated Total Reflectance (ATR) or other material appropriate test method.
5. Thermogravimetric Analysis samples shall be at least 50 microns minimum thickness.

[a] A cured or liquid adhesive only sample is to be provided. If not possible, cured adhesive on the film shall be provided for IR analysis.

[b] A cured sample is to be provided, if possible. As an alternative, a 50 gram (2 oz) liquid sample (with accompanying MSDS) shall be provided for IR analysis.

[c] See 8.1.4 for sample construction requirements when evaluating the properties of materials related to the intended application.

Documents
Document Sharing Hub
Full document details: UL 746F 2025

**Table 8.2**
**Dielectric Film Material Performance Profile Index and Relative Thermal Index Test Program and Sample Requirements**

| Property | Sample dimensions length by width, mm (inch) | Film thickness | Adhesive thickness | Minimum number of samples | Applicable materials | For method refer to: |
|---|---|---|---|---|---|---|
| Short Term Performance Profile Tests | | | | | | |
| High Current Arc Ignition (HAI)[d] | 125 x 13 (5 x 0.5) | Min | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |
| High Current Arc Ignition (HAI)[d] | 125 x 13 (5 x 0.5) | Max | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |
| High Current Arc Ignition (HAI)[d] | 125 x 13 (5 x 0.5) | Min | Min | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| High Current Arc Ignition (HAI)[d] | 125 x 13 (5 x 0.5) | Min | Max | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| High Current Arc Ignition (HAI)[d] | 125 x 13 (5 x 0.5) | Max | Min | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| High Current Arc Ignition (HAI)[d] | 125 x 13 (5 x 0.5) | Max | Max | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| Hot Wire Ignition (HWI)[d] | 125 x 13 (5 x 0.5) | Min | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |
| Hot Wire Ignition (HWI)[d] | 125 x 13 (5 x 0.5) | Max | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |
| Hot Wire Ignition (HWI)[d] | 125 x 13 (5 x 0.5) | Min | Min | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| Hot Wire Ignition (HWI)[d] | 125 x 13 (5 x 0.5) | Min | Max | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| Hot Wire Ignition (HWI)[d] | 125 x 13 (5 x 0.5) | Max | Min | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| Hot Wire Ignition (HWI)[d] | 125 x 13 (5 x 0.5) | Max | Max | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| Comparative Tracking Index (CTI) | 100 x 100 (4 x 4) | Max | – | c | F, B | UL 746F, 8.1.4, UL 746A |
| Comparative Tracking Index (CTI) | 100 x 100 (4 x 4) | Max | Max | c | F, FA, B | UL 746F, 8.1.4, UL 746A |
| Dielectric Strength (DS) | 100 x 100 (4 x 4) | Max | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |
| Dielectric Strength (DS) | 100 x 100 (4 x 4) | Max | Max | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| Volume Resistivity (VR) | 100 x 100 (4 x 4) | Max | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |
| Volume Resistivity (VR) | 100 x 100 (4 x 4) | Max | Max | 10 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| Moisture Absorption (MA) | 75 x 25 (3 x 1) | Max | – | 5 | F, B | UL 746F, 8.1.4, UL 746A |
| Moisture Absorption (MA) | 75 x 25 (3 x 1) | Max | Max | 5 | F, FA, B | UL 746F, 8.1.4, UL 746A |
| Tensile Strength (Bias Cut)[a,b] | 250 x 25 (10 x 1) | Min | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |

**Table 8.2 Continued on Next Page**

Documents
Document Sharing Hub
Full document details: UL 746F 2025

## Table 8.2 Continued

| Property | Sample dimensions length by width, mm (inch) | Film thickness | Adhesive thickness | Minimum number of samples | Applicable materials | For method refer to: |
|---|---|---|---|---|---|---|
| Tensile Strength (Bias Cut)[a,b] | 250 x 25 (10 x 1) | Max | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |
| Tensile Strength (Machine Cut)[a,b] | 250 x 25 (10 x 1) | Min | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |
| Tensile Strength (Machine Cut)[a,b] | 250 x 25 (10 x 1) | Max | – | 10 | F, B | UL 746F, 8.1.4, UL 746A |
| Long Term Thermal Aging Tests | | | | | | |
| 4 Point Thermal Aging Tensile Strength | 250 x 25 (10 x 1) | Min | – | 400 | F, B | UL 746F, 8.1.4, UL 746A and UL 746B |
| 4 Point Thermal Aging Dielectric Strength | 100 x 100 (4 x 4) | Min | – | 400 | F, B | UL 746F, 8.1.4, UL 746A and UL 746B |
| Secondary Flame | 125 x 13 (5 x 0.5) | Min | – | 60 | F, B | UL 746F, 8.1.4, UL 94 and UL 746B |
| Secondary Flame | 125 x 13 (5 x 0.5) | Max | – | 60 | F, B | UL 746F, 8.1.4, UL 94 and UL 746B |

Material Types:

F – Base Dielectric Film (film only, no adhesive. Includes adhesiveless “sputtered” or “cast on” materials.)

FA – Adhesive Coated Base Dielectric Film (film and adhesive)

B – Bonding Film (film and adhesive or adhesive only.)

NOTES:

1. All the samples shall be in the machine (grain) longitudinal direction unless specified otherwise.
2. All the samples shall be double-sided unless single sided material is intended for production.
3. All the samples are to be prepared declad by completely etching a metal clad sheet, where applicable.

[a] Film only shall be evaluated for Tensile Strength in the minimum and maximum thickness.

[b] Tensile Strength samples shall be prepared in the machine and transverse direction for non-reinforced or non-woven reinforced films. Tensile Strength samples shall be prepared in the bias and machine direction for woven reinforced films.

[c] If CTI samples are submitted at a thickness less than 2.5 mm (0.10 inch), the required number of samples varies depending on the thickness of the film. The number of samples shall be increased in order to provide 10 samples built up to the required 2.5 mm (0.10 inch) testing thickness.

[d] See 8.1.4 for sample construction requirements when evaluating the properties of materials related to the intended application.

Documents
Document Sharing Hub
Full document details: UL 746F 2025